

IN THE CLAIMS:

Please cancel claim 7 without prejudice or disclaimer, amend claims 6, 9 and 11, and add new claims 12-15.

Claims 1-5. (Previously canceled)

Claim 6 (Currently amended): A radical copolymerizable unsaturated resin composition comprising

_____ a compatibilizing agent,

_____ an addition polymerized polymer,

_____ a radical copolymerizable unsaturated resin, and

_____ a polymerizable unsaturated monomer,

wherein the compatibilizing agent is a graft copolymer (A) which contains a styrene ~~monomer repeat units~~ as a principal component, ~~and has~~ said graft copolymer (A) having:

_____ a principal chain (A1) ~~consisting of that is~~ a copolymer ~~with comprising~~ a (meth)acrylate ~~monomer repeat units and the styrene repeat units;~~ and

_____ a side chain (A2) selected from a ring-opening polymerized polyether side chain consisting of a polyoxyalkylene ether, a polyester side chain, and a polycarbonate side chain,

_____ the side chain (A2) being bonded to the principal chain (A1), and

_____ the amount of the graft copolymer (A) being within a range of 0.1-10 parts by weight based on the total of the amount of the radical copolymerizable unsaturated resin and the amount of the addition polymerized polymer as 100 parts by weight.

Claim 7 (canceled)

Claim 8 (Previously amended): A radical copolymerizable unsaturated resin composition according to claim 6, wherein the radical copolymerizable unsaturated resin is an unsaturated polyester.

Claim 9 (Currently amended): A molding material comprising the radical copolymerizable unsaturated resin composition of claim 7 6.

C¹
Claim 10 (Original): A molded article comprising the molding material of claim 9.

Claim 11 (Currently amended): A radical copolymerizable unsaturated resin composition according to claim 7 6, wherein the radical copolymerizable unsaturated resin is an unsaturated polyester.

C²
Claim 12 (New): A radical copolymerizable unsaturated resin composition according to claim 6, wherein the principal chain (A1) comprises 70-99.9% by weight of the styrene repeat units and 0.1-30% by weight of other unsaturated repeat units including the (meth)acrylate repeat units.

Claim 13 (New): A radical copolymerizable unsaturated resin composition according to claim 6, wherein the side chain (A2) comprises oxyethylene units in an amount within a range of 60-100% by weight.

C2
Claim 14 (New): A radical copolymerizable unsaturated resin composition according to claim 6, wherein the weight ratio (A1/A2) of the principal chain (A1) to the side chain (A2) is within a range of 70/30-30/70.

Claim 15 (New): A radical copolymerizable unsaturated resin composition according to claim 6, wherein the amount of the graft copolymer (A) is within a range of 0.5-3 parts by weight based on the total of the amount of the radical copolymerizable unsaturated resin and the amount of the addition polymerized polymer as 100 parts by weight.